



GANTS BIOTAC 100 % Nitrile

DESCRIPTIF

Gant sans latex
 Gant non triboélectrique
 Utilisation salle blanche
 Conditionné par 100
 100 % Nitrile



PROPRIETES ELECTRIQUES

Système de qualité : conforme ISO 9001
 Inspection : certifiée ISO 2859
 Instructions de stockage : à conserver dans un endroit sec

REFERENCES	TAILLES
01-0501-70006	S
01-0501-70007	M
01-0501-70008	L
01-0501-70009	XL

CHARACTERISTICS	VALUE	TEST METHOD
Freedom From Holes	1.5 AQL	EN 374-2:2003
Minimum Length (mm/inches)	290/11.4	EN 420:2003
Single Wall Thickness Minimum (mm)	Cuff: 0.08 Palm: 0.11 Finger Tip: 0.17	EN 455-2:2009
Force At Break During Shelf Life	≥9	EN 455-2:2009

PALM WIDTHS (mm) ± 5mm						
SIZE	XSmall	Small	Medium	Large	XLarge	XXLarge
mm	75	85	95	105	115	119
TEST METHOD				EN455-2:2009		

PARTICLES				TYPICAL PARTICLE COUNT				TEST METHOD
≥ 0.5µm(counts/cm ²)				<1500				IEST-RP-CC005.3
TYPICAL EXTRACTABLE IONS								TEST METHOD
ANIONS	Fluoride	Chloride	Nitrite	Bromide	Nitrate	Phosphate	Sulphate	IEST-RP-CC005.3
(µg/cm ²)	ND	0.11	ND	ND	0.26	ND	0.017	
CATIONS	Lithium	Sodium	Ammonium	Potassium	Calcium	Magnesium	Zinc	
(µg/cm ²)	ND	0.029	0.011	0.03	0.31	0.002	ND	
ND = Not Detected, NT = Not Tested								